


CRITICAL P2T VALUE COMPUTATINN FOR EXPLOSIVES USING THE 1/1
SHEAR BAND INITIA. (U) ARMY BALLISTIC RESEARCH LAB
ABERDEEN PROVING GROUND MD E H WALKER JAN 85

BRL-MR-3425 SBI-AD-F300 557

F/G 19/1

NL

END



MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS 1963 A

**B
R
L****AD-A149 990****AD****MEMORANDUM REPORT BRL-MR-3425**

**CRITICAL P^2T VALUE COMPUTATION FOR
EXPLOSIVES USING THE SHEAR
BAND INITIATION MODEL**

Evan Harris Walker**January 1985**

DTIC
ELECTE
FEB 4 1985
S D
B

DTIC FILE COPY**APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED.**

**US ARMY BALLISTIC RESEARCH LABORATORY
ABERDEEN PROVING GROUND, MARYLAND**

Destroy this report when it is no longer needed.
Do not return it to the originator.

Additional copies of this report may be obtained
from the National Technical Information Service,
U. S. Department of Commerce, Springfield, Virginia
22161.

The findings in this report are not to be construed as an official
Department of the Army position, unless so designated by other
authorized documents.

The use of trade names or manufacturers' names in this report
does not constitute indorsement of any commercial product.

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

DD FORM 1 JAN 73 1473 EDITION OF 1 NOV 68 IS OBSOLETE

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

20. Abstract (continued)

Frey at BRL has recently proposed a shear band mechanism as a source of hot spots in explosives subjected to rapid shearing. If the shear band mechanism is generally applicable, it must be possible to relate it to the critical values of P^2T for different explosives. This would allow one to calculate this important sensitivity criterion from the mechanical and thermodynamic properties of explosives. Gibbons at BRL has observed shear banding in shocked explosives; however, the Frey model treats the shear velocity as an input parameter. Expressions have now been derived for the shear velocity across a band generated by shock loading, and for the density and dimensions of the shear bands. Using the thermodynamic properties of the explosive, this initial heating can be followed to full detonation. Similarly, by making the shock pressure a function of time to model stress relief waves in the shocked explosive, one can compute the conditions for failure to detonate. Thus, we obtain a complete model of shock initiated detonation based on more fundamental physical properties of explosives. This capability should make the control of sensitivity in explosives a more exact procedure.

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

TABLE OF CONTENTS

	Page
LIST OF ILLUSTRATIONS.	5
I. INTRODUCTION	7
II. FREY'S SHEAR BAND MODEL.	7
III. SHEAR BAND PRODUCTION BY SHOCK LOADING IN HETEROGENEOUS EXPLOSIVES	9
IV. SHEAR VELOCITY FOR TWO CONSTITUENT EXPLOSIVES.	12
V. SHEAR BAND DENSITY	14
VI. CONCLUSIONS.	17
REFERENCES	19
DISTRIBUTION LIST.	21

DTIC
ELECTE
FEB 4 1985
B

Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution	
Avail	
Dist	A-1



LIST OF ILLUSTRATIONS

Figure		Page
1.	Schematic of the Sources of Shear Bands According to Frey's Model.	8
2.	Scanning Electron Micrograph of Shock Loaded Comp B	10
3.	Schematic Representation of a Shock Passing Through a Heterogeneous Material.	11
4.	Shear Velocity Required to Achieve Thermal Explosion Criterion of 1000°K in 1 μ s as a Function of Pressure (curve "a"), after Frey, and a Plot of Equation (5) for the Shear Velocity Generated in Comp B Due to the Shock Pressure	13
5.	Schematic of Shear Band Formation	15

I. INTRODUCTION

The P^2T criterion for the onset of detonation, first proposed by Walker and Wasley,¹ has become a central issue in the study of detonation mechanics. Although the criterion has been criticized, most recently by Moulard,² the criterion has been extensively employed and supported by experimental studies.³⁻⁷ E. H. Walker⁸ has recently employed the criterion successfully in a study comparing fratricide initiation in a variety of artillery shells with differing explosive fills. Thus, any satisfactory understanding of detonation onset will require an understanding of the P^2T mechanism.

A number of studies⁹⁻¹³ have sought to derive or calculate values for the P^2T criterion, but none has provided a strictly physical theory free of *ad hoc* assumptions as to the origin and distribution of initiation sites, "hot spots", or the assumed initiating temperature distribution behind the shock front. Ramsey¹⁴ argues such an assumption is not important to derive the relation $P^2T = \text{const.}$, but evaluating this constant for different explosives must depend on the mechanism that gives rise to the initial heating and evolution of heat in the explosive. Howe, et al¹⁵ have shown that shock initiation of detonation consists of two processes: an ignition process and a build up process. They present evidence that the build up to detonation is controlled by a heat transfer dominated grain burning process. The ignition process appears to arise from shock induced "hot spots."

The necessity of the hot spot concept of Bowden¹⁶ and Eyring¹⁷ arises from the fact that under shock initiation conditions the bulk temperature of the explosive is much too low to initiate decomposition. Various mechanisms have been proposed to account for the hot spots controlling the ignition process. Bowden and Yoffe¹⁶ proposed adiabatic compression of gas as the principal mechanism, but also discussed plastic work in solid explosives as a mechanism. Mader¹⁸ studied the mechanism of direct heating of the explosive by void closure; Seeley¹⁹ has suggested jetting during void closure as the mechanism for hot spot formation; and Delpuech, et al²⁰ suggest shock induced free radical formation as playing the critical role in the initiation process.

II. FREY'S SHEAR BAND MODEL

Recently Frey²¹ has proposed a shear band theory for hot spot formation. Frey suggested these shear bands might arise during void closure or during shock induced displacement of the explosive near irregularities at the explosive-container wall interface, as shown in Figure 1. Starting with this hypothesis, Frey showed that shearing under pressure could lead to sufficiently rapid heating of the explosive to generate hot spots in the explosive adequate to give rise to initiation of the explosive. However, the shear velocities indicated by the shear band mechanisms shown in Figure 1 do not depend on the explosive material properties. As such, the P^2T criterion as a property of the explosive would be difficult to understand.




Figure 1. Schematic of the Sources of Shear Bands According to Frey's Model. (A) Shear bands produced in front of cubical and spherical cavities. (B) Velocity gradient producing shear bands near irregular interface.

Until recently, shear bands in shock loaded explosives had not been observed. Gibbons²² has recently obtained scanning electron micrographs showing an extensive shear band structure in shock loaded comp B, Figure 2. The comp B also shows evidence of incipient reaction of the TNT matrix in the area of the shear bands. From the location of these shear bands, it is apparent that the shear bands do not result from either cavity collapse or container wall irregularities. The shear bands could also arise from the shear stress field in the explosive produced by deformation of the explosive container. However, that flow field depends primarily on the characteristics of the container and the container's response to impulsive loading, and only to a lesser degree on the properties of the comp B fill. Such an origin for shears leading to initiation of the explosive would not be likely to involve the P^2T criterion. Another cause for the occurrence of the shear bands is required. A mechanism for shear band production that makes use of Frey's shear band theory and that provides a procedure for the computation of P^2T criterion values for explosives is presented below. In a separate report,²³ we derive the P^2T criterion based on the model presented here.

III. SHEAR BAND PRODUCTION BY SHOCK LOADING IN HETEROGENEOUS EXPLOSIVES

Assume a shock passes through a material, such as comp B, consisting of grains of one material, RDX, embedded in a matrix of a second material, here TNT. The pressure p behind the shock is given in terms of the density ρ , sound velocity u , and particle velocity v by

$$p = \rho_0 uv \quad . \quad (1)$$

Although the pressure is the same in both the RDX grains and the TNT matrix, since the impedance, ρu , differs in the two materials, the particle velocity will differ in the two constituents, as indicated in Figure 3. Table 1 shows the densities, sound velocities and particle velocities for RDX and TNT for a 2.5 GPa shock pressure. The resulting velocity difference is

$$v_s = v_1 - v_2 \quad . \quad (2)$$

From Table 1 this gives 70 m/s.

TABLE 1

Densities, Sound Velocities, and Particle Velocities for the
Constituents of Comp B at 2.5 GPa*

	ρ_0 (g/cm ³)	u (km/s)	v (km/s)
RDX	1.80	3.53	0.395
TNT	1.61	3.34	0.465

*Computed from shock Hugoniot data in The LLNL Explosives Handbook, B. M. Dobratz, University of California, Livermore, CA 94550. See table 7.5.

A



B



Figure 2. Scanning Electron Micrograph of Shock Loaded Comp B. Magnitude of the shock was about 2.5 GPa. The grains are RDX particles which are embedded in the TNT matrix. The shear bands run principally between the RDX grains, although some shear bands run through the RDX grains. This area was discolored brown by incipient reaction of the TNT. (A) Magnification is 750X; (B) Enlargement of upper right of (A) at a magnification of 1500X.




Figure 3. Schematic Representation of a Shock Passing Through a Heterogeneous Material. The shock velocities differ in the two materials as do the particle velocities. As a result, a velocity gradient will develop across these materials giving rise to shear.

It is to be noted that even in a single constituent explosive, a similar result will occur. The propagation velocity for a sound wave differs along various crystal orientations. In such materials, for individual grains, $u_{(100)}$ will differ significantly from $u_{(111)}$ or $u_{(010)}$ for example (where the subscripts refer to the principal axes along the crystal grains of the explosive.) Thus, we would obtain various shear velocities depending on crystal orientations. For a crystal having the (111) plane parallel to the (100) plane in a neighboring crystal we would have

$$v_s = v_{(100)} - v_{(111)} . \quad (3)$$

Unfortunately, sound velocity data along different crystal axes for explosives is too sketchy for our present needs, so we will confine our interest to two constituent explosives.

We will also limit our treatment to the case in which the shear takes place in the matrix. In general, where the effective shear strength of the explosive approximates the shear strength of the matrix, we may treat the process of shear formation as taking place in the matrix. Where the shear strength approximates the shear strength of the grains, shear formation should be calculated for the grains. In other cases, we must make calculations for shearing that can occur in either the matrix or the grains. In such cases, the smaller of the calculated P^2T values obtained is to be taken for the critical value characterizing the explosive. Thus, generalization of the present approach can be achieved in a straight forward way.

It should be noted that shear band formation described here constitutes the incipient mechanism for shear failure. Large scale mechanical failure of the explosive is associated with the arrival of relief waves from free surfaces (failure of the explosive's container walls, for example). The arrival of these relief waves lead to the growth of the incipient shears into larger shears that ultimately connect to form macroscopic cracks in the explosive.

IV. SHEAR VELOCITY FOR TWO CONSTITUENT EXPLOSIVES

Writing ρ_1, u_1 for the density and sound velocity in the matrix and ρ_2, u_2 for the density and sound velocity for the included grains we write

$$v_s = p \frac{\rho_2 u_2 - \rho_1 u_1}{\rho_1 u_1 \rho_2 u_2} \quad (4)$$

where a negative result indicates shearing results from a slower matrix particle velocity. This velocity is the overall shear velocity between the two constituents of the explosive. It is not the shear band shear velocity however, as it does not take account of the number of shear bands (on average) in the matrix lying between two grains. As the shock passes between two grains, the displaced material will strain until relieved by the development of one or more shear bands.




Figure 4. Shear Velocity Required to Achieve Thermal Explosion Criterion of 1000°K in $1 \mu\text{s}$ as a Function of Pressure (curve "a"), after Frey and a Plot of Equation (5) for the Shear Velocity Generated in Comp B Due to the Shock Pressure. The intercept point occurs at $v_s = 40.8 \text{ m/s}$, $p = 1.42 \text{ GPa}$. Curve "c" is discussed in Section V. It incorporates the correction for the number of shear bands developed by the shear in matrix material as given by Equation 11 for v_b . The intercept occurs at $v_b = 57 \text{ m/s}$, $p = 1.50 \text{ GPa}$.

In Frey's analysis, the shear velocity occurs as a parameter dependent on the circumstances of cavities and container irregularities. In the present case, we see that the velocity difference is dependent on the physical properties of the explosive. In the case of comp B, v_s (km/s) is given, approximately, in terms of the pressure p (GPa) by

$$v_s = 2.79 \times 10^{-2} p \quad (5)$$

Frey²⁴ shows that there is a functional relation between shear velocity and the shock pressure, where time to reach a critical ignition temperature appears as a parameter, Figure 4. With Frey's computed results for the shear velocity versus shock pressure for TNT as shown in Figure 4, and the relation between shock pressure and shear velocity for the TNT matrix in comp B, as given in Equation 5, we can solve to obtain the shock pressure leading to a given ignition temperature in a specified time. From Figure 4, we obtain a solution of $v_s = 40.8$ m/s and $p = 1.42$ GPa. Assuming the ignition temperature of 1000°K as used by Frey, we calculate a P^2T criterion of

$$P^2T)_{\text{crit}} = 2.02 \times 10^{12} (\text{Pa}^2\text{s}) \quad (6)$$

The result is to be compared with an experimental value of $4.41 \times 10^{12} \text{Pa}^2\text{s}$. The difference in values obtained here arises from the fact that the shear velocity in Equation 5 is not the shear band shear velocity, but instead the overall shear velocity between the grains of RDX and matrix of TNT. Let us now turn to the question of the shear band density which will allow us to obtain the shear band shear velocity.

V. SHEAR BAND DENSITY

To obtain the shear band shear velocity v_b , it is necessary to derive the density of the shear bands in the matrix material. Consider the material displacement as shown in Figure 5. After the shock passes through the explosive, a shear gradient will develop due to the resistance to shear at the matrix-grain interface. In a time t assumed to be very short (i.e., before shear banding develops) the material behind the shock will assume, approximately, a rhomboidal displacement as seen in Figure 5. Figure 5 shows one of these rhomboidal sections broken into several incipient shear bands of width d and strain δd such that

$$\delta d = \frac{\text{total strain in time } t}{\text{number of shear bands}} = \frac{v_s t}{D/d} \quad (7)$$

The failure angle θ_{max} at which shear occurs is related to the strain δd by

$$\frac{\delta d}{d} = \theta_{\text{max}} \quad (8)$$

Where θ_{max} is a property of the material. Of course, Figure 5 idealizes the regularity of the overall process.




Figure 5. Schematic of Shear Band Formation. (a) Displacement of matrix material relative to grains due to passage of a shock, where it is assumed the difference in shock particle velocity developed into a velocity gradient as expected for viscous flow in a channel. The displacement indicated by the two rhomboidal regions indicates strains at an early time after passage of the shock. (b) Schematic of a rhomboidal region giving shear band and displacement dimensions just before formation of the bands due to development of slide planes. (c) Resulting displacement of material in the rhomboid of (b) as the critical angle θ_{max} occurs.

The time at which this shearing occurs depends on the propagation of stress relief into the material as shear banding develops. Thus, in a time t such a relief wave can propagate only a distance $u_1 t$. This means that the next nearest shear will be located at most a distance $u_1 t$ away. Since the process is more nearly stochastic, the average value for the separation of the shear bands will be half $u_1 t$. Since that distance is also d , we have

$$\frac{1}{2} u_1 t = d. \quad (9)$$

Therefore, from Equations 7, 8, and 9, we have

$$d = \frac{\theta_{\max} D u_1}{2 v_s}. \quad (10)$$

Now substituting from Equation 4 for v_s we obtain

$$d = \frac{\theta_{\max} D u_1 \rho_1 u_1 \rho_2 u_2}{2 p (\rho_2 u_2 - \rho_1 u_1)}. \quad (11)$$

The number of shear bands in the gap between grains, n^* is, approximately,

$$n^* = 2D/d = \frac{4p (\rho_2 u_2 - \rho_1 u_1)}{\theta_{\max} u_1 \rho_1 u_1 \rho_2 u_2}. \quad (12)$$

θ_{\max} is given in terms of the shear modulus G and shear strength σ_{\max} by σ_{\max}/G . The shear modulus can also be expressed in terms of the Young's elastic modulus E and Poisson's ratio ν by $\frac{1}{2}E/(1+\nu)$. Thus,

$$\theta_{\max} = 2 (1+\nu) \sigma_{\max}/E. \quad (13)$$

The value of the shear band shear velocity v_b is given by dividing v_s by n , where

$$n = n^*/2. \quad (14)$$

Since both v_s and n are linear in p , v_b is independent of p . We have from Equations (4) and (12)

$$v_b = \frac{1}{2} u_1 \theta_{\max}. \quad (15)$$

For $E = 5.4$ GPa, $\nu = 0.3$ and $\sigma_{\max} = 0.07$ GPa, we have from Equation (13)

$$\theta_{\max} = 0.034 \quad (16)$$

for TNT. With u_1 of 3.34 km/s as given in Table 1, we obtain from Equation (15), $v_b = 57$ m/s for the shear band shear velocity in the TNT matrix material.

From Figure 4, we see this yields an intercept at a shock pressure of 1.30 GPa. This value of the pressure acting for 1 μ s yields for the computed P^2T value

$$P^2T)_{crit} = 1.69 \times 10^{12} \text{ Pa}^2\text{s} . \quad (17)$$

This value is somewhat lower than the experimental value of $4.4 \times 10^{12} \text{ Pa}^2\text{s}$. However, the criterion for initiation of the explosive used in Frey's calculation is similarly approximate. It should be pointed out that as treated here, this is only an initiation criterion, and not a detonation criterion, as time must be allowed for the incipient burn of the explosive at these hot spots to generate self sustaining pressures. In a separate report,²⁵ this problem is considered in some detail and shown to contribute only a small contribution to the P^2T value we have here. Thus, using an expression for the shear band shear velocity under shock loading conditions, we can employ Frey's shear band theory to calculate $P^2T)_{crit}$ from the properties of explosive materials.

VI. CONCLUSIONS

A theory relating shock loading to the development of shear bands in explosives has been presented. This theory together with Frey's shear band theory for the development of hot spots due to shear heating along these shear bands makes it possible to compute $P^2T)_{crit}$ values for explosives from the mechanical and thermodynamic properties of the explosive.

REFERENCES

1. F. E. Walker and R. J. Wasley, "Critical Energy for the Shock Initiation of Heterogeneous Explosives," Explosivestoffe 17, 9, (1969).
2. H. Moulard, "Critical Conditions for Shock Initiation of Detonation by Small Projectile Impact," Seventh Symposium (International) on Detonation, pp. 316-324, 16-19 June 1981, NSWC/MP-82-334, Naval Surface Weapons Center, Annapolis, MD. Moulard's experimental results can be understood as arising from a reduced shock pressure in the coalesced region and not a breakdown of the P^2T criterion.
3. P. Howe, R. Frey, B. Taylor and V. Boyle, "Shock Initiation and the Critical Energy Concept," Sixth Symposium (International) on Detonation, pp. 11-19, ACR-221, US Government Printing Office, Washington, DC 20402.
4. E. F. Gittings, "Initiation of a Solid High Explosive by a Short Duration Shock," Fourth Symposium (International) on Detonation, pp. 373-380, ACR-126, US Government Printing Office, Washington, DC 20402.
5. E. L. Lee and C. M. Tarver, "Phenomenological Model of Shock Initiation in Heterogeneous Explosives," Phys Fluids, 23, 2362-2372, (1980).
6. R. C. Weingart, R. K. Jackson, C. A. Honodel and R. S. Lee, "Shock Initiation of PBX 9404 by Electrically Driven Flyer Plates," Tenth Symposium on Explosives and Pyrotechnics, preprint VCRL-82162 January 1979.
7. Y. de Longueville, C. Fauquignon, H. Moulard, "Initiation of Several Condensed Explosives by a Given Duration Shock Wave," Sixth Symposium (International) on Detonation, pp. 105-114, ACR-221, US Government Printing Office, Washington, DC 20402.
8. E. H. Walker, "Computer Model of Shield Design for Artillery Shell Fratricide Suppression," BRL Report (in Press).
9. See Refs. 1, 5, 7
10. B.O. Trott, R. G. Jung, "Effect of Pulse Duration on the Impact Sensitivity of Solid Explosives," Fifth Symposium (International) on Detonation, pp. 191-205, ACR-184, US Government Printing Office, Washington, DC 20402.
11. J. Wackerle, J. O. Johnson, and P. M. Halleck, "Shock Initiation of High-Density PETN," Sixth Symposium (International) on Detonation, pp. 20-28, ACR-221, US Government Printing Office, Washington, DC 20402.
12. D. B. Hayes, "A P^2T Denotation Criterion from Thermal Explosion Theory," Sixth Symposium (International) on Detonation, pp. 76-81, ACR-221, US Government Printing Office, Washington, DC 20402.
13. W. H. Andersen, "Model of Impact Ignition and Explanation of Critical Shock Initiation Energy II Application," Seventh Symposium (International) on Detonation, pp. 459-465, 16-19 June 1981, NSWC/MP-82-334, Naval Surface Weapons Center, Annapolis, MD.



REFERENCES (continued)

14. J. B. Ramsey, "Short Duration Shock Wave Initiation of Solid Explosives," Acta Astronautica, 6, 771, (1979).
15. See Ref. 3.
16. F. P. Bowden and A. D. Yoffe, Initiation and Growth of Explosions in Liquids and Solids, Cambridge University Press (1952).
17. H. Eyring, R. E. Powell, G. H. Duffrey, and R. B. Darlin, Chemical Review, 45, 69, (1949).
18. C. L. Mader, Phys Fluids, 8, 10, (1965).
19. L. B. Seeley, "A Proposed Mechanism for Shock Initiation of Low Density Granular Explosives," Proceedings of the Fourth Electric Initiator Symposium (1963).
20. A. Delpuech, J. Cherville, and C. Michaud, "Molecular Electronic Structure and Initiation of Secondary Explosives," Seventh Symposium (International) on Detonation, pp. 65-74, 16-19 June 1981, Annapolis, MD.
21. R. B. Frey, "The Initiation of Explosive Charges by Rapid Shear," Seventh Symposium (International) on Detonation, pp. 36-42, 16-19 June 1981, Annapolis, MD.
22. G. Gibbons, Jr., Observations of Impact Generated Shear Bands in Composition-B Ballistic Research Laboratory Memorandum Report (in press).
23. E. H. Walker, "Derivation of the P^2T Criterion (in Closed Form) Based on the Frey Shear Band Mechanism," Ballistic Research Laboratory Technical Report ARBRL-TR-02544, January 1984. (ADA-137530)
24. See Ref. 21, Figure 7.
25. See Ref. 23, pg 12-13.

DISTRIBUTION LIST

<u>No. of</u> <u>Copies</u>	<u>Organization</u>	<u>No. of</u> <u>Copies</u>	<u>Organization</u>
12	Administrator Defense Technical Info Center ATTN: DTIC-DDA Cameron Station Alexandria, VA 22314	1	Commander Armament R&D Center US Army AMCCOM ATTN: SMCAR-LCN, Dr. P. Harris Dover, NJ 07801
1	Chairman DOD Explosives Safety Board ATTN: Dr. T. Zaker Room 856-C Hoffman Bldg 1 2461 Eisenhower Avenue Alexandria, VA 22331	1	Commander US Army Armament, Munitions and Chemical Command ATTN: SMCAR-ESK-L Rock Island, IL 61299
1	Commander US Army Materiel Command ATTN: AMCDRA-ST 5001 Eisenhower Avenue Alexandria, VA 22333	1	Director Benet Weapons Laboratory Armament R&D Ctr/ US Army AMCCOM ATTN: SMCAR-LCB-TL Watervliet, NY 12189
1	Commander Armament R&D Center US Army AMCCOM ATTN: SMCAR-TDC Dover, NJ 07801	1	Commander US Army Aviation Research and Development Command ATTN: AMSAV -E 4300 Goodfellow Boulevard St. Louis, MO 63120
1	Commander Armament R&D Center US Army AMCCOM ATTN: SMCAR-TSS Dover, NJ 07801	1	Director US Army Air Mobility Research and Development Laboratory Ames Research Center Moffett Field, CA 94035
1	Commander Armament R&D Center US Army AMCCOM ATTN: SMCAR-LCE, Dr. R. F. Walker Dover, NJ 07801	1	Commander US Army Communications Rsch and Development Command ATTN: AMSEL-ATDD Fort Monmouth, NJ 07703
1	Commander Armament R&D Center US Army AMCCOM ATTN: SMCAR-LCE, Dr. N. Slagg Dover, NJ 07801	1	Commander US Army Electronics Research and Development Command Technical Support Activity ATTN: DELSD-L Fort Monmouth, NJ 07703
1	HQDA DAMA-ART-M Washington, DC 20310	1	Commander US Army Development & Employment Agency ATTN: MODE-TED-SAB Fort Lewis, WA 98433

DISTRIBUTION LIST (continued)

<u>No. of</u> <u>Copies</u>	<u>Organization</u>	<u>No. of</u> <u>Copies</u>	<u>Organization</u>
1	Commander US Army Missile Command ATTN: AMSMI-R Redstone Arsenal, AL 35898	1	Commander Naval Sea Systems Command ATTN: Mr. R. Beauregard, SEA 64E Washington, DC 20360
1	Commander US Army Missile Command ATTN: AMSMI-YDL Redstone Arsenal, AL 35898	1	Commander Naval Explosive Ordnance Disposal Facility ATTN: Technical Library Code 604 Indian Head, MD 20640
1	Commander US Army Missile Command ATTN: AMSME-RK, Dr. R.G. Rhoades Redstone Arsenal, AL 35898	1	Commander Naval Research Lab ATTN: Code 6100 Washington, DC 20375
1	Commander US Army Tank Automotive Command ATTN: AMSTA-TSL Warren, MI 48090	1	Commander Naval Surface Weapons Center ATTN: Code G13 Dahlgren, VA 22448
1	Director US Army TRADOC Systems Analysis Activity ATTN: ATAA-SL White Sands Missile Range NM 88002	9	Commander Naval Surface Weapons Center ATTN: Mr. L. Roslund, R122 Mr. M. Stosz, R121 Code X211, Lib E. Zimet, R13 R.R. Bernecker, R13 J.W. Forbes, R13 S.J. Jacobs, R10 K. Kim, R13 Dr. C. Dickinson Silver Spring, MD 20910
1	Commandant US Army Infantry School ATTN: ATSH-CD-CSO-OR Fort Benning, GA 31905	4	Commander Naval Weapons Center ATTN: Dr. L. Smith, Code 3205 Dr. A. Amster, Code 385 Dr. R. Reed, Jr., Code 388 Dr. K. J. Graham, Code 3835 China Lake, CA 93555
1	Commander US Army Research Office ATTN: Chemistry Division P.O. Box 12211 Research Triangle Park, NC 27709		
1	Commander Office of Naval Research ATTN: Dr. J. Enig, Code 200B 800 N. Quincy Street Arlington, VA 22217		

DISTRIBUTION LIST (continued)

<u>No. of Copies</u>	<u>Organization</u>	<u>No. of Copies</u>	<u>Organization</u>
1	Commander Naval Weapons Station NEDED ATTN: Dr. Louis Rothstein, Code 50 Yorktown, VA 23691		<u>Aberdeen Proving Ground</u> Dir, USAMSAA ATTN: AMXSY-D AMXSY-MP , H. Cohen
1	Commander Fleet Marine Force, Atlantic ATTN: G-4 (NSAP) Norfolk, VA 23511		Cdr, USATECOM ATTN: AMSTE-TO-F Cdr, CRDC, AMCCOM ATTN: SMCCR-RSP-A SMCCR-MU SMCCR-SPS-IL
1	Commander AFRPL ATTN: Mr. R. Geisler, Code AFRPL MKPA Edwards AFB, CA 93523		
1	AFWL/SUL Kirtland AFB, NM 87117		
1	Commander US Army BMD Advanced Technology Center ATTN: Dr. David C. Sayles P.O. Box 1500 Huntsville, AL 35807		
1	Director Lawrence Livermore National Lab University of California ATTN: Dr. M. Finger Livermore, CA 94550		
1	Director Los Alamos Scientific Laboratory ATTN: John Ramsey P.O. Box 1663 Los Alamos, NM 87544		
1	Director Sandia National Lab ATTN: Dr. J. Kennedy Albuquerque, NM 87115		

USER EVALUATION SHEET/CHANGE OF ADDRESS

This Laboratory undertakes a continuing effort to improve the quality of the reports it publishes. Your comments/answers to the items/questions below will aid us in our efforts.

1. BRL Report Number _____ Date of Report _____
2. Date Report Received _____
3. Does this report satisfy a need? (Comment on purpose, related project, or other area of interest for which the report will be used.) _____

4. How specifically, is the report being used? (Information source, design data, procedure, source of ideas, etc.) _____

5. Has the information in this report led to any quantitative savings as far as man-hours or dollars saved, operating costs avoided or efficiencies achieved etc? If so, please elaborate. _____

6. General Comments. What do you think should be changed to improve future reports? (Indicate changes to organization, technical content, format, etc.) _____

CURRENT ADDRESS	_____
	Name

	Organization

	Address

	City, State, Zip

7. If indicating a Change of Address or Address Correction, please provide the New or Correct Address in Block 6 above and the Old or Incorrect address below.

OLD ADDRESS	_____
	Name

	Organization

	Address

	City, State, Zip

(Remove this sheet along the perforation, fold as indicated, staple or tape closed, and mail.)

----- FOLD HERE -----

Director
US Army Ballistic Research Laboratory
ATTN: AMXBR-OD-ST
Aberdeen Proving Ground, MD 21005-5066




NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE. \$300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 12062 WASHINGTON, DC
POSTAGE WILL BE PAID BY DEPARTMENT OF THE ARMY

Director
US Army Ballistic Research Laboratory
ATTN: AMXBR-OD-ST
Aberdeen Proving Ground, MD 21005-9989



----- FOLD HERE -----

END

FILMED

3-85

DTIC